

**APPLICATION FOR
UNITED STATES LETTERS PATENT**

entitled

**METHOD OF REDUCING ALUMINUM FLUORIDE DEPOSITS IN PLASMA
ETCH REACTOR**

by

**Duane Outka
15 Gazania Terrace
Fremont, CA 94536**

**Yousun Kim
1715 Shamrock Ave.
Santa Clara, CA 95051**

**Anthony Chen
1142 Mountain Blvd.
Oakland, CA 94611**

and

**John Daugherty
34717 Woodhue Ter.
Fremont, CA 94555**

**Attorney Docket No. 015290-496
Lam Reference No.: P0739
BURNS, DOANE, SWECKER & MATHIS, L.L.P.
P.O. Box 1404
Alexandria, Virginia 22313-1404
(703) 836-6620**

**METHOD OF REDUCING ALUMINUM FLUORIDE DEPOSITS IN
PLASMA ETCH REACTOR**

Field of the Invention

5 [0001] The invention relates to techniques for reducing deposits in plasma etch reactors.

Background of the Invention

10 [0002] Current semiconductor processing equipment, including plasma reactors (both etch and chemical vapor deposition (CVD) type), create non-volatile byproducts that deposit on the chamber walls. These byproducts change the chemical composition of the chamber wall. Build-up of these deposits can cause process drift, particle contamination, and a short chamber maintenance cycle because of the necessity for frequent wet cleans.

15 [0003] During processing of semiconductor wafers it is conventional to carry out periodic in-situ cleaning of plasma etch and CVD reactors to alleviate the above mentioned problems. U.S. Patent No. 5,129,958 discloses a method for cleaning a CVD deposition chamber in a semiconductor wafer processing apparatus wherein fluorine residues in the chamber, left from a prior fluorine plasma cleaning step, are contacted with one or more reducing gases such as silane (SiH_4), ammonia, hydrogen, phosphine (PH_3), diborane (B_2H_6), and arsine (AsH_3). Another technique for cleaning and conditioning interior surfaces of

20

plasma CVD reactors is disclosed in commonly owned U.S. Patent No. 5,647,953, the subject matter of which is hereby incorporated by reference. In the past these cleans were done with a wafer in the chamber to cover the electrode, but it has become more common to do waferless cleans.

- 5 **[0004]** Other techniques for cleaning plasma reaction chambers are disclosed in U.S. Patent Nos. 4,657,616; 4,786,352; 4,816,113; 4,842,683, 4,857,139; 5,006,192; 5,129,958; 5,158,644 and 5,207,836 and in Japanese Laid-Open Patent Publication Nos. 57-201016; 61-250185, 62-214175, 63-267430 and 3-62520, and in commonly owned U.S. Patent No. 5,356,478. For instance, in order to remove
- 10 SiO_x deposits, a fluorine-containing gas energized into a plasma has been used to clean interior surfaces of the chamber. Fluorine residues remaining after the reactor cleaning can be removed by passing a reducing gas such as hydrogen (H₂), silane (SiH₄), ammonia (NH₃), phosphine (PH₃), diborane (B₂H₆) or arsine (AsH₃) through the reactor.
- 15 **[0005]** In process chambers that etch aluminum metal, some of the byproduct can be composed of aluminum fluoride or other solid material consisting in part of aluminum and fluorine atoms. While an aluminum etch chamber requiring an etch process that uses a fluorine-containing gas (e.g., CF₄, CHF₃) is one example of a source that may produce aluminum fluoride, other processes can as well. Since
- 20 many processing chambers are constructed of aluminum metal, almost any process that uses a fluorine-containing gas can produce aluminum fluoride. A process to eliminate aluminum fluoride from the chamber would reduce the incidence of

defects, chamber processing drift, and/or chamber downtime for cleaning and maintenance.

Summary of the Invention

[0006] This invention provides a method of cleaning a plasma etch chamber in which substrates are processed, comprising the steps of introducing a cleaning gas comprising a chlorine-containing gas into the chamber, energizing the cleaning gas into a plasma state, forming dissociated and undissociated reactive species in the chamber and reacting these species with deposits on the interior surfaces of the chamber. After the cleaning step, a conditioning step may be performed.

[0007] In a first preferred embodiment, a method of cleaning aluminum fluoride deposits from a plasma reaction chamber after etching a semiconductor substrate is provided. A cleaning gas comprising at least BCl_3 is supplied to a plasma etch reactor. When energized into a plasma state, the cleaning gas forms dissociated and undissociated BCl_3 and the undissociated BCl_3 reacts with aluminum fluoride deposits in the plasma etch reactor and cleans the deposits from the interior surfaces. The cleaning gas may comprise BCl_3/O_2 or $\text{BCl}_3 + \text{Cl}_2/\text{O}_2$ wherein a concentration of Cl_2 may be supplied to obtain a desired degree of BCl_3 dissociation.

[0008] In a second preferred embodiment, a method of reducing aluminum fluoride deposits from a plasma reaction chamber during plasma etching of a semiconductor substrate is provided. The etching step includes a main etch and an overetch. An etching gas during the main etch includes $\text{C}_x\text{F}_y\text{H}_z$ wherein $x \geq 1$, $y \geq$

1 and $z \geq 0$ and aluminum fluoride deposits are formed during the main etch. The etching gas during the overetch includes at least BCl_3 which is energized into a plasma state and forms dissociated and undissociated BCl_3 . During the over etch, the undissociated BCl_3 reduces the aluminum fluoride deposits in the plasma etch reactor. Subsequent to the etching step, the substrate can be removed from the plasma etch reactor and a cleaning step can be carried out. The cleaning gas may comprise O_2 , Cl_2/O_2 , BCl_3/O_2 or $\text{BCl}_3 + \text{Cl}_2/\text{O}_2$ wherein a concentration of Cl_2 may be supplied to obtain a desired degree of BCl_3 dissociation.

[0009] It is further provided that the method may include a plasma etching step in which a main etching gas comprising $\text{C}_x\text{F}_y\text{H}_z$ wherein $x \geq 1$, $y \geq 1$, and $z \geq 0$, Cl_2 , N_2 and BCl_3 and an over etching gas comprising Cl_2 and BCl_3 is utilized to etch a semiconductor wafer.

Brief Description of the Drawings

[0010] Figure 1 is a schematic of a test piece;

[0011] Figure 2 shows the relationship between deposition thickness and CHF_3 gas flow rate;

[0012] Figures 3A-C show the thickness of the chamber deposits at three sample locations in the chamber;

[0013] Figure 4 shows the thickness of the chamber deposits at three sample locations in the chamber under three different combinations of etching and waferless autoclean processes;

[0014] Figure 5 shows the endpoint trace of three variations of the base waferless autoclean with CHF_3 additive metal etch;

[0015] Figure 6 shows the thickness of the chamber deposits at three sample locations in the chamber when Cl_2 is included in an O_2 waferless autoclean step;

5 and

[0016] Figure 7 shows the thickness of the chamber deposits at three sample locations in the chamber under various waferless autoclean recipes.

Detailed Description of the Invention

[0017] The invention provides an economical and efficient method of reducing deposits in a plasma etch reactor in which substrates are processed. The method includes supplying an etching gas to the plasma etch reactor and reducing deposits in the plasma etch chamber by energizing the etching gas into a plasma state such that a portion of the etching gas dissociates and the undissociated gas reacts with the deposits in the plasma etch reactor.

15 [0018] In a first preferred embodiment, the invention provides a method of cleaning a plasma etch reactor by removing aluminum fluoride deposits. A cleaning gas with at least BCl_3 is supplied to the plasma etch reactor. Upon energizing into a plasma state, at least a portion of the BCl_3 gas is dissociated and the undissociated BCl_3 reacts with aluminum fluoride deposits. The process may
20 be accomplished in a waferless autoclean (WAC).

[0019] In a second preferred embodiment, fluoride deposits are reduced during plasma etching of a semiconductor substrate. The etching step includes a main

etch and an overetch. An etching gas during the main etch includes $C_xF_yH_z$ wherein $x \geq 1$, $y \geq 1$ and $z \geq 0$ and aluminum fluoride deposits are formed during the main etch. The etching gas during the overetch includes at least BCl_3 which is energized into a plasma state and forms dissociated and undissociated BCl_3 .

5 During the over etch, the undissociated BCl_3 reduces the aluminum fluoride deposits in the plasma etch reactor. Subsequent to the etching step, the substrate can be removed from the plasma etch reactor and a cleaning step can be carried out. The cleaning gas may comprise O_2 , Cl_2/O_2 , BCl_3/O_2 or BCl_3+Cl_2/O_2 wherein a concentration of Cl_2 may be supplied to obtain a desired degree of BCl_3 dissociation.

10 [0020] Additionally, the methods of the invention may be conducted in any suitable plasma etch reactor. For example, the plasma etch reactor may be an ECR plasma reactor, an inductively coupled plasma reactor, a capacitively coupled plasma reactor, a helicon plasma reactor or a magnetron plasma reactor. A more specific example of a plasma etch reactor suitable for practicing the invention includes an inductively coupled plasma reactor having an antenna which inductively couples radio frequency energy into an interior of the plasma etch reactor through a dielectric member. The plasma etch reactor preferably includes a bottom electrode in the interior on which a semiconductor substrate can be supported. During the cleaning step, the antenna may be powered with 100 to 3000 watts and the bottom electrode can be powered with up to 3000 watts.

15 [0021] In an additional preferred embodiment, the invention provides a waferless plasma process for cleaning chambers used for plasma etching an

aluminum (Al) containing film stack. The process for plasma etching of Al produces a by-product which deposits throughout the reactor. Eventually this by-product reaches a thickness where it no longer sticks to the reactor wall and particles are shed which contaminate the substrate being etched. When this happens, the reactor must be opened and cleaned with a wet clean process.

[0022] For example, a WAC may be utilized in etch chambers to increase the mean time between cleaning (MTBC) and to reduce the possible process shifts contributed by chamber deposits. The process of preparing a reactor for cleaning, along with the actual clean process and the steps required to condition the chamber following an open chamber clean can require a substantial amount of time. To maximize productivity in a wafer fab, it is desirable to extend the time between opening the chamber to do such open chamber cleans. One method for doing this has been to run plasma cleans, which are capable of reducing the etch by-product deposited in the chamber resulting in a extended time between open chamber cleans. However, since plasma cleans alter the chamber condition by removing the reactor deposits, there is typically a process shift following the plasma clean.

As a result, the aluminum etch rate, etch profiles, and feature CDs (critical dimension) can shift outside of the acceptable range for the device being manufactured. If a plasma clean is used, wafers may be cycled through the chamber to recondition the walls prior to etching product wafers. An example of a conditioning process is disclosed in commonly owned U.S. Patent Application No. 09/469,286, the subject matter of which is hereby incorporated by reference.

[0023] In processes wherein a wafer is needed in the chamber for conditioning, a special wafer type may also be needed. This limits the applicability of plasma clean processes for Al etching in a production environment because it would be disruptive to production flows to have to load special wafers into the chamber and run a conditioning process after a plasma clean. As a result, in production, plasma cleans would not be used and the reactors would need to be opened more frequently for long wet clean procedures. Thus, the reactor availability advantage of using plasma cleans to extend the wet clean time is negated by the burden of reconditioning the chamber with a special wafer type.

[0024] The invention provides a process that can be run without a wafer in the chamber to clean by-products of the Al etch from the surfaces of the etch reactor. One of the commonly used additive gases for Al etch is CHF_3 which yields AlF_3 in the chamber deposits. Alternative main etching gases may include $\text{C}_x\text{F}_y\text{H}_z$ wherein $x \geq 1$, $y \geq 1$, and $z \geq 0$, Cl_2 , N_2 , and BCl_3 . $\text{C}_x\text{F}_y\text{H}_z$ may be in the form CF_4 , CHF_3 or mixtures thereof.

[0025] Previously, metal etch chambers were not candidates for WAC due to the type of deposits resulting from the Al etch. For example, AlF_3 may form as a byproduct of CHF_3 used during the etching process. AlF_3 is a highly stable, non-reactive, and non-volatile material that is thermodynamically unfavorable to remove. The success of WAC for metal etch seemed improbable because it was thought that removal of AlF_3 with WAC would be unfeasible. However, according to the invention, deposits formed during Al etch can be removed using BCl_3 as a cleaning gas in a WAC process.

[0026] A wet clean of an aluminum etch chamber was performed followed by an evaluation of the cleaning process. A Lam TCP™ 9600PTX™ etcher was used for testing cleaning processes with and without WAC. In addition to not having a chamber liner, the test chamber had special test hardware installed at locations of a
5 vertically movable "uniformity ring" (U-ring) surrounding the wafer, the gas distribution oplate (GDP) and at the chamber wall.

[0027] Figure 1 shows a test piece 100 used throughout the evaluation. A representative test piece 100 may be cleaved from SiO₂ wafers to form coupons 105. A mask 110 may be placed on the coupon 105 to allow height differentiation
10 after exposing the test piece 100 to in-chamber deposits. After the chamber and its parts were cleaned, three test pieces 100 were attached with non-thermoplastic polyimide tape. A representative polymeric (e.g. non-thermoplastic polyimide-based) composition which is suitable for this purpose is a commercial product sold under the trademark "KAPTON" by E.I. DuPont de Nemours and
15 Company of Wilmington, Del. (USA). The test pieces 100 were positioned at predetermined locations (the transfer module side of the U-ring, the gas distribution plate (GDP), and the chamber wall on the side of the transfer module).

[0028] After securing the test pieces 100, the chamber was pumped down and 25-50 etch cycles were conducted with appropriate Open Area wafers and recipes.
20 Note that there is no conditioning of the chamber. After the wafers are cycled, the chamber was pump purged. After the chamber had been sufficiently pump purged, the chamber was opened and the test pieces 100 collected. Upon extraction, the masks 110 were taken off and the step height difference between the masked area

and the exposed area where the byproducts were deposited was measured six times (three measurements each side) with a KLA-Tencor P-2 Long Scan Profiler. An average of these six measurements was calculated and designated as the deposit thickness for the location of the test piece 100. The masks 110 were carefully removed so as not to disturb the exposed area and the thickness was measured immediately after extraction from the chamber to minimize the effect of humidity on the deposits, which might otherwise flake off or change. Deposit elemental composition data was collected with a Hitachi 4100 EDS SEM. SiO₂ was factored out of the composition and the thickness analysis because the test pieces are also made of SiO₂.

[0029] In the evaluation, 50% and 100% Open Area wafers were used as etch substrates. All 100% Open Area wafers had Al thickness of 10,000 Å. 50% Open Area wafers had two Al thicknesses: 10,000 Å and 5,000 Å. The 10,000 Å wafers were used to reproduce chamber conditions during metal etch where the wafers were etched only partway into the Al. The 5,000 Å wafers were used to replicate chamber conditions during metal etch and overetch steps and were etched all the way through the Al and into the oxide layer.

[0030] Process recipes used to determine dependence of thickness and composition of chamber deposits on the percent Open Area of a wafer and CHF₃ flow with and without WAC are listed in Tables 1 and 2:

[0031] Table 1: Recipes Used for CHF₃ Additive Chemistry Coupon Study

Type of Etch	Etch Recipe
Main Etch Recipe	1) 12mT/ 800 W _{TCP} / 130W _b / 120Cl ₂ / 70BCl ₃ / X ^a CHF ₃ / 60 seconds
Base WAC Recipe	1) 30mT/ 800 W _{TCP} / 100W _b /200 O ₂ / 3 seconds 2) 30mT/ 800 W _{TCP} / 4 W _b / 200 O ₂ / 12 seconds 3) 30mT/ 800 W _{TCP} / 4W _b / 160 Cl ₂ / 10 seconds

^aX determined from Table 2; Bottom Electrode Temperature = 50°C;
Chamber Temperature = 70°C

[0032] Table 2: Matrix for % Wafer Open Area and CHF₃ Flow

Open Area	CHF ₃ (sccm)	WAC
100 %	5	With and Without
50 %	5, 10, 16	With and Without

CHF₃ Additive Metal Etch without WAC

[0033] The effect of the amount of CHF₃ on chamber deposits during metal etch was evaluated. Figure 2 shows deposit thickness as a function of CHF₃ flow rate. Here, the deposit thickness is the average of the thickness at the three locations. From Figure 2, a linear relationship between CHF₃ flow and deposit thickness is observed. Deposit thickness increases with increasing CHF₃ flow, which indicates that CHF₃ is a source for chamber deposit. Thus, the chamber deposit thickness, and possibly even MTBC, may be controlled and manipulated by the flow of CHF₃.

[0034] Figures 3A-C show deposit thickness at three locations for different CHF₃ flow rates with and without WAC using the base WAC recipe. The composition of the deposit is dependent on CHF₃ flow and there is a considerable

difference in concentration of Al and F between different CHF₃ flows. Large amounts of Al and F are present in the deposits with 16 sccm CHF₃. In contrast, only a trace amount of Al and F was observed in the deposits with 5 sccm CHF₃.

[0035] At the location of the U-ring, column A of Figure 3A indicates that the

5 deposit thickness was about 2 μm after the etch step using 16 sccm CHF₃ and column B indicates that the deposit thickness was reduced to about 1.4 μm after the WAC wherein O₂ gas was used as the cleaning gas. Measurements of B, Cl, Si, Al, F, O and C contents of the deposits indicate that about one-third of the deposit after the etch step and after the cleaning step was comprised of Al and F
10 and that at least some of the Al and F is in the form of aluminum fluoride.

Column C indicates that the deposit thickness was about 1.6 μm after the etch step using 10 sccm CHF₃ and column D indicates that the deposit thickness was reduced to about 0.8 μm after the WAC wherein O₂ gas was used as the cleaning gas. Measurements of B, Cl, Si, Al, F, O and C contents of the deposits indicate
15 very little of the deposit after the etch step and after the cleaning step was

comprised of Al and F. Column E indicates that the deposit thickness was about 1 μm after the etch step using 5 sccm CHF₃ and column F indicates that the deposit thickness was reduced to about 0.25 μm after the WAC wherein O₂ gas was used as the cleaning gas. Measurements of B, Cl, Si, Al, F, O and C contents of the
20 deposits indicate no detectable amount of the deposit after the etch step and after the cleaning step was comprised of Al and F.

[0036] At the location of the GDP, column A of Figure 3B indicates that the deposit thickness was about 1.6 μm after the etch step using 16 sccm CHF₃ and

column B indicates that the deposit thickness was reduced to about $1.25\mu\text{m}$ after the WAC wherein O_2 gas was used as the cleaning gas. Measurements of B, Cl, Si, Al, F, O and C contents of the deposits indicate that about two-thirds of the deposit after the etch step and after the cleaning step was comprised of Al and F and that at least some of the Al and F is in the form of aluminum fluoride.

Column C indicates that the deposit thickness was about $1.25\mu\text{m}$ after the etch step using 10 sccm CHF_3 and column D indicates that the deposit thickness was reduced to about $0.75\mu\text{m}$ after the WAC wherein O_2 gas was used as the cleaning gas. Measurements of B, Cl, Si, Al, F, O and C contents of the deposits indicate that about 50 to 60% of the deposit after the etch step and after the cleaning step was comprised of Al and F. Column E indicates that the deposit thickness was about $0.85\mu\text{m}$ after the etch step using 5 sccm CHF_3 and column F indicates that the deposit was removed after the WAC wherein O_2 gas was used as the cleaning gas. Measurements of B, Cl, Si, Al, F, O and C contents of the deposits indicate no detectable amount of the deposit after the etch step and after the cleaning step was comprised of Al and F.

[0037] At the position of the chamber wall, column A of Figure 3C indicates that the deposit thickness was about $2.5\mu\text{m}$ after the etch step using 16 sccm CHF_3 and column B indicates that the deposit thickness was reduced to about $1.4\mu\text{m}$ after the WAC wherein O_2 gas was used as the cleaning gas. Measurements of B, Cl, Si, Al, F, O and C contents of the deposits indicate that about 50% of the deposit after the etch step and after the cleaning step was comprised of Al and F and that at least some of the Al and F is in the form of aluminum fluoride.

Column C indicates that the deposit thickness was about $1.3\ \mu\text{m}$ after the etch step using 10 sccm CHF_3 and column D indicates that the deposit thickness was reduced to about $0.8\ \mu\text{m}$ after the WAC wherein O_2 gas was used as the cleaning gas. Measurements of B, Cl, Si, Al, F, O and C contents of the deposits indicate that about 50% of the deposit after the etch step and after the cleaning step was comprised of Al and F. Column E indicates that the deposit thickness was about $0.7\ \mu\text{m}$ after the etch step using 5 sccm CHF_3 and column F indicates that the deposit thickness was reduced to about $0.35\ \mu\text{m}$ after the WAC wherein O_2 gas was used as the cleaning gas. Measurements of B, Cl, Si, Al, F, O and C contents of the deposits indicate that about 30% of the deposit after the etch step was comprised of Al and F and that Al and F were not detected in the deposit after the WAC.

[0038] Figure 2 also depicts the influence of wafer Open Area on deposit thickness with and without WAC with a 5 sccm CHF_3 additive metal etch. Effects of different Open Areas on chamber deposits was evaluated since, in addition to other Al containing parts, Al of the AlF_3 can originate from the wafer surface. Most metal product wafers currently have 30 ~ 40% Open Area. However, with decreasing critical dimension and geometry, the Open Area is expected to increase. Figure 2 reveals that the deposit thickness did not significantly vary between 50% Open Area wafers and 100% Open Area wafers at a CHF_3 flow rate of 5 sccm.

CHF_3 Additive Metal Etch with WAC

[0039] Figure 2 reveals that the WAC may decrease the deposit thickness and that the efficiency of the WAC may be limited by the CHF_3 flow. CHF_3 flow

may not only influence the deposit thickness; it may also have a significant effect on the composition of the deposit. The amount of Al and F in the deposit is affected by the amount of CHF₃ present during metal etch. Figures 3A-C reveal that as CHF₃ flow rate increases the Al and F in the deposit also increases.

5 Although, a small flow rate of CHF₃ (≤ 5 sccm) may reduce or eliminate AlF₃ in the deposit, possibly due to the limited Al and F deposits at this low flow rate, the current WAC may be insufficient for eliminating deposits formed when using ≥ 5 sccm CHF₃ during the Al etch. Therefore, it may be concluded that the efficiency of the current WAC is limited by the amount of CHF₃ present during metal etch.

10 Effects of Over Etch step with CHF₃ Additive Metal Etch

[0040] An Over Etch (OE) step after the Main Etch (ME) may affect the composition of the chamber deposits. Table 3 shows the recipes used to study the effects of the OE step. The ME may include C_xH_yF_z as a component wherein $x \geq 1$, $y \geq 1$, and $z \geq 0$. An example of representative gas is CHF₃. The OE may be carried out with a C_xH_yF_z-free gas, e.g. BCl₃ and/or Cl₂ as components. The wafers used were 50% Open Area Aluminum wafers (10,000 Å Al).

[0041] Table 3: Recipes Used to Study the Effects of the Over Etch Step

Type of Etch	Etch Recipe
ME: Main Etch Recipe	1) 12mT/ 800 W _{TCP} / 130W _b / 120Cl ₂ / 70BCl ₃ / 10 CHF ₃ / EndPt (40~45 seconds)
OE: Over Etch Recipe	1) 12mT/ 700 W _{TCP} / 120W _b / 50Cl ₂ / 50BCl ₃ / 40 seconds
WAC Recipe	1) 30mT/ 800 W _{TCP} / 100W _b / 200 O ₂ / 3 seconds 2) 30mT/ 800 W _{TCP} / 4W _b / 200 O ₂ / 12 seconds 3) 30mT/ 800 W _{TCP} / 4W _b / 160 Cl ₂ / 10 seconds

Bottom Electrode Temperature = 50°C


Chamber Temperature = 70°C

[0042] Figure 4 shows that when the base WAC was added after each wafer was processed with ME and OE, almost all of the deposit is eliminated. The amount of Al and F in the chamber deposit is surprisingly decreased with the addition of the $C_xH_yF_z$ -free OE step even without WAC. The OE step may eliminate the Al and F in the deposit, leaving mostly volatile substance. This was observed at all three test piece locations and suggests that the ME and OE process is efficient at removing both Al and F deposits and volatile matter.

[0043] The mechanism of the OE that results in AlF_3 removal may be the plasma chemistry. In a preferred embodiment, the OE chemistry contains BCl_3 and Cl_2 . For example, BCl_3 may be reacting with AlF_3 to form a volatile product:



[0044] The exchange of Cl and F might continue to transform AlF_3 to volatile $AlCl_3$:



[0045] It is also possible that the change in the byproducts or etch substrates might contribute to a change in chamber condition that allows AlF_3 removal. The byproducts of the wafer changes during the OE since layers such as an oxide layer may undergo etching after the Al is cleared.

[0046] In Figure 4, the coupons at the locations of the U-ring, the GDP and the chamber wall were subjected to three etching conditions, i.e., main etch only (ME w/o WAC), main etch and overetch (MEOE w/o WAC), and main etch, overetch

and waferless cleaning (MEOE w/ WAC). The process conditions of the ME, OE and WAC are set forth in Table 3.

[0047] At the location of the U-ring, column A of Figure 4 indicates that the deposit thickness was about $0.6\ \mu\text{m}$ after the main etch using 10 sccm CHF_3 ,

5 column B indicates a deposit thickness of about $0.7\ \mu\text{m}$ when the main etch is followed by an overetch using BCl_3 and Cl_2 , and column C indicates that the deposit thickness was reduced to about $0.05\ \mu\text{m}$ after the main etch and overetch are followed by a WAC wherein O_2 gas was used as the cleaning gas.

Measurements of B, Cl, Si, Al, F, O and C contents of the deposits indicate that
10 about one-third of the deposit after the main etch step was comprised of Al and F, a trace of the deposit after the overetch was comprised of Al and F, and that Al and F were not detected in the remaining deposit after the WAC.

[0048] At the location of the GDP, column D of Figure 4 indicates that the deposit thickness was about $0.6\ \mu\text{m}$ after the main etch using 10 sccm CHF_3 ,

15 column E indicates a deposit thickness of about $0.4\ \mu\text{m}$ when the main etch is followed by an overetch using BCl_3 and Cl_2 , and column F indicates that the deposit was removed after the main etch and overetch are followed by a WAC wherein O_2 gas was used as the cleaning gas. Measurements of B, Cl, Si, Al, F, O and C contents of the deposits indicate that about two-thirds of the deposit after
20 the main etch step was comprised of Al and F, and that Al and F were not detected in the remaining deposit after the overetch or after the WAC.

[0049] At the location of the chamber wall, column G of Figure 4 indicates that the deposit thickness was about $0.9\ \mu\text{m}$ after the main etch using 10 sccm CHF_3 ,

column H indicates a deposit thickness of about $0.3\ \mu\text{m}$ when the main etch is followed by an overetch using BCl_3 and Cl_2 , and column I indicates that the deposit thickness was removed after the main etch and overetch are followed by a WAC wherein O_2 gas was used as the cleaning gas. Measurements of B, Cl, Si, Al, F, O and C contents of the deposits indicate that about one-half of the deposit after the main etch step was comprised of Al and F, and that Al and F were not detected in the remaining deposit after the overetch or after the WAC.

Alternative WAC Chemistry

[0050] Different WAC chemistries were examined to better understand the mechanism and to optimize the WAC process. The desired effect of the optimal WAC should eliminate as much of the chamber deposits including AlF_3 as possible. Table 4 lists five different WAC recipes used for this evaluation. The wafers used were 50% Open Area Aluminum wafers ($10,000\ \text{\AA}\ \text{Al}$). 10 sccm CHF_3 was chosen for the ME recipe since 10 sccm corresponds to the flow of CHF_3 used in conventional Al main etch recipes and 10 sccm of CHF_3 contributes Al and F to the chamber deposit, thereby allowing evaluation of the impact of WAC process variations on these deposits.

[0051] Figure 5 depicts the endpoint trace of the three different O_2/Cl_2 WAC recipes with 10 sccm CHF_3 additive metal etch. Figure 6 illustrates the deposit thickness of the O_2/Cl_2 WAC with 10 sccm CHF_3 and an O_2 only WAC with 10 sccm CHF_3 . In the endpoint trace of the base WAC, the O_2 part of WAC has a negative slope while the Cl_2 part is almost flat suggesting that the Cl_2 part of the WAC may not remove any polymer. The thickness data (Figure 6) illustrates no

significant difference between the O₂/Cl₂ WAC and the O₂ only WAC, further suggesting the small contribution of the Cl₂ step to polymer removal. When the gases were reversed from the base WAC recipe, the deposit thickness results exhibit the same trends as for the base WAC and again suggest the limited Cl₂ influence on deposits. The results indicate that the Cl₂ step may or may not be desirable depending on the effects of the Cl₂ step on process shifts such as etch rate, CD, and profile. For example, the Cl₂ concentration can influence the BCl₃ dissociation thereby providing undissociated BCl₃ to the AlF₃ reaction as represented in equations 1 and 2.

10 [0052] In Figure 6, the coupons at the locations of the U-ring, the GDP and the chamber wall were subjected to two etching conditions, i.e., a main etch using 10 sccm CHF₃, no overetch, and a WAC with O₂/Cl₂ or WAC with only O₂.

[0053] At the location of the U-ring, column A of Figure 6 indicates that the deposit thickness was about 0.8 μm when the main etch using 10 sccm CHF₃ is followed by a WAC using O₂ and Cl₂ and column B indicates a deposit thickness of about 0.8 μm when the main etch is followed by a WAC using only O₂.

Measurements of B, Cl, Si, Al, F, O and C contents of the deposits indicate that about one-half of the deposit was comprised of Al and F after either WAC.

[0054] At the location of the GDP, column C of Figure 6 indicates that the deposit thickness was about 0.7 μm when the main etch using 10 sccm CHF₃ is followed by a WAC using O₂ and Cl₂ and column D indicates a deposit thickness of about 0.8 μm when the main etch is followed by a WAC using only O₂.

Measurements of B, Cl, Si, Al, F, O and C contents of the deposits indicate that about one-half of the deposit was comprised of Al and F after either WAC.

[0055] At the location of the chamber wall, column E of Figure 6 indicates that the deposit thickness was about $0.8\ \mu\text{m}$ when the main etch using 10 sccm CHF_3 is followed by a WAC using O_2 and Cl_2 and column F indicates a deposit thickness of about $0.8\ \mu\text{m}$ when the main etch is followed by a WAC using only O_2 .

Measurements of B, Cl, Si, Al, F, O and C contents of the deposits indicate that about one-half of the deposit was comprised of Al and F after either WAC.

[0056] Different gases such as Cl_2 and BCl_3 were substituted in the base WAC to find the optimal WAC chemistry that can maximize elimination of chamber polymers along with Al and F. Figure 7 illustrates deposit thickness at three test locations under four WAC recipes. From Figure 7, it is observed that the addition of BCl_3 in the WAC decreased the deposit thickness on test pieces. At the U-ring, deposit thickness was reduced from $>0.6\ \mu\text{m}$ to $<0.2\ \mu\text{m}$ and no trace of Al or F was detected in the deposits. This result is consistent with the proposed mechanism for AlF_3 removal. The deposition at the GDP was also reduced, but to a lesser extent and the deposit retained detectable levels of Al and F.

[0057] In Figure 7, the coupons at the locations of the U-ring, the GDP and the chamber wall were subjected to four etching conditions set forth in Table 4, i.e., a main etch using 10 sccm CHF_3 , no overetch, and four different WAC treatments including a base WAC, a Cl_2/O_2 WAC, a BCl_3/O_2 WAC and a $\text{BCl}_3+\text{Cl}_2/\text{O}_2$ WAC.

[0058] At the location of the U-ring, column A of Figure 7 indicates that the deposit thickness was about $0.8\ \mu\text{m}$ with the base WAC, column B indicates that the deposit thickness was about $0.7\ \mu\text{m}$ with the Cl_2/O_2 WAC, column C indicates that the deposit thickness was about $0.1\ \mu\text{m}$ with the BCl_3/O_2 WAC, and column D indicates that the deposit thickness was about $0.1\ \mu\text{m}$ with the $\text{BCl}_3 + \text{Cl}_2/\text{O}_2$ WAC. Measurements of B, Cl, Si, Al, F, O and C contents of the deposits indicate that about one-half of the deposit was Al + F after the base WAC and Cl_2/O_2 WAC whereas Al and F were not detected after the BCl_3/O_2 WAC and a $\text{BCl}_3 + \text{Cl}_2/\text{O}_2$ WAC.

[0059] At the location of the GDP, column E of Figure 7 indicates that the deposit thickness was about $0.7\ \mu\text{m}$ with the base WAC, column F indicates that the deposit thickness was about $1\ \mu\text{m}$ with the Cl_2/O_2 WAC, column G indicates that the deposit thickness was about $0.7\ \mu\text{m}$ with the BCl_3/O_2 WAC, and column H indicates that the deposit was removed with the $\text{BCl}_3 + \text{Cl}_2/\text{O}_2$ WAC.

Measurements of B, Cl, Si, Al, F, O and C contents of the deposits indicate that about one-half of the deposit was Al + F after the base WAC, the Cl_2/O_2 WAC and the BCl_3/O_2 WAC whereas Al and F were not detected after the $\text{BCl}_3 + \text{Cl}_2/\text{O}_2$ WAC.

[0060] At the location of the chamber wall, column I of Figure 7 indicates that the deposit thickness was about $0.9\ \mu\text{m}$ with the base WAC, column J indicates that the deposit thickness was about $1\ \mu\text{m}$ with the Cl_2/O_2 WAC, column K indicates that the deposit thickness was about $0.8\ \mu\text{m}$ with the BCl_3/O_2 WAC, and column L indicates that the deposit thickness was about $0.7\ \mu\text{m}$ after the

$\text{BCl}_3 + \text{Cl}_2/\text{O}_2$ WAC. Measurements of B, Cl, Si, Al, F, O and C contents of the deposits indicate that about one-half of the deposit was Al + F after the base WAC, the Cl_2/O_2 WAC, the BCl_3/O_2 WAC and the $\text{BCl}_3 + \text{Cl}_2/\text{O}_2$ WAC.

[0061] The $\text{BCl}_3 + \text{Cl}_2/\text{O}_2$ WAC was used to mimic the OE recipe, since it was shown above that the OE step followed by O_2 WAC eliminated almost all of the deposit. In the tests run to develop the data shown in Figure 7, the pressure was lowered, Cl_2 was added and the etch time of the first step of the WAC was increased to 40 seconds. As shown in Figure 7, this WAC recipe resulted in the elimination of deposits at the GDP and reduced U-ring deposits to $<0.2 \mu\text{m}$ in thickness. As in the BCl_3/O_2 WAC, no trace Al or F was detected in these deposits.

[0062] The thickness and composition of the test pieces from the chamber changed little between the different WAC chemistries. This may be caused by the plasma's inability to effectively reach the chamber walls or insufficient WAC time.

According to the results of the OE recipe followed by O_2 WAC, it is possible to completely eliminate deposits on the test pieces mounted in the chamber. One difference between the conditions of the OE with O_2 WAC and the $\text{BCl}_3 + \text{Cl}_2/\text{O}_2$ WAC is time. During the OE study, the ME to OE time ratio was almost 1:1 (~ 43 seconds to 40 seconds) versus 3:2 (60 seconds to 40 seconds) during $\text{BCl}_3 + \text{Cl}_2/\text{O}_2$ WAC evaluation. Under sufficiently long time, both the BCl_3/O_2 WAC and the $\text{BCl}_3 + \text{Cl}_2/\text{O}_2$ WAC should reduce deposit thickness and lower the amounts of Al and F in the deposits.

[0063] Table 4: Recipes used for alternative WAC chemistry study

Type of Etch	Etch Recipe
Main Etch Recipe	1) 12mT/ 800 W _{TCP} / 130W _b / 120Cl ₂ /70BCl ₃ / 10 CHF ₃ / 60 seconds
Base WAC Recipe (O ₂ /Cl ₂ WAC)	1) 30mT/800 W _{TCP} / 100 W _b / 200 O ₂ / 3 seconds 2) 30mT/800 W _{TCP} /4 W _b / 200 O ₂ / 12 seconds 3) 30mT/800 W _{TCP} /4 W _b / 160 Cl ₂ / 10 seconds
Cl ₂ /O ₂ WAC Recipe	1) 30mT/800 W _{TCP} / 100 W _b / 200 O ₂ / 3 seconds 2) 30mT/800 W _{TCP} / 4 W _b / 160 Cl ₂ / 12 seconds 3) 30mT/800 W _{TCP} / 4 W _b / 200 O ₂ / 10 seconds
BCl ₃ /O ₂ WAC Recipe	1) 30mT/800 W _{TCP} / 100 W _b / 100 Cl ₂ / 3 seconds 2) 30mT/800 W _{TCP} / 4 W _b / 100 BCl ₃ / 12 seconds 3) 0mT/0 W _{TCP} /0 W _b / 5 seconds 4) 30mT/800 W _{TCP} / 100 W _b / 200 O ₂ / 3 seconds 5) 30mT/800 W _{TCP} / 4 W _b / 200 O ₂ / 10 seconds
BCl ₃ +Cl ₂ /O ₂ WAC Recipe	1) 12mT/800 W _{TCP} / 100 W _b / 100 Cl ₂ / 3 seconds 2) 12mT/800 W _{TCP} / 4 W _b / 50 BCl ₃ / 50 Cl ₂ / 40 seconds 3) 0mT/0 W _{TCP} / 0 W _b / 5 seconds 4) 30mT/800 W _{TCP} / 100 W _b / 200 O ₂ / 3 seconds 5) 30mT/800 W _{TCP} / 4 W _b / 200 O ₂ / 12 seconds

Bottom Electrode Temperature = 50°C

Chamber Temperature = 70°C

[0064] While the invention has been described in detail with reference to specific embodiments thereof, it will be apparent to those skilled in the art that various changes and modifications can be made, and equivalents employed, without departing from the scope of the appended claims.